

1 & 2mm Texture - Technical Data Sheet

Product Description

Supercoat™ Texture is an Acrylic, thixotropic paste with graded aggregate for use over Acrylic and Concrete base coats.

Specifications

MSDS	002 - Version 1.0
Appearance	Off White
Vehicle Type	Acrylic
Pigmentation	Titanium Dioxide
Solvent	Water
Finish	Flat
Colour	Tintable
Touch dry time	4 hours at 20°C
Time to 2nd coat	24 hours at 20°C
Wet film thickness 1mm	1000 microns
Wet film thickness 2mm	2000 micron
Solids Content	45% (Silica not included)
Viscosity	95 KU (+/- 3) (Silica not included)
Specific Gravity	1.24 (Silica not included)
Usual number of coats	1
Toxicity	No added Chromites or Lead
Thinning & cleaning	Water
Coverage 1mm	1m ² /L (depending on substrate profile and applicator)
Coverage 2mm	0.5m ² /L (depending on substrate profile and applicator)
Pail type & size	Plastic 15L

Please Note

Do not apply at temperatures below 10°C or if it is likely to drop below 10°C during drying/curing time. Do not apply at temperatures over 30°C or if it is likely to go over 30°C during drying/curing time. Softens at temperatures over 70°C.

Manufacturer

Ironbark Technology Ltd
PO Box 2398, Dunedin, New Zealand.
Phone (03) 456 4222
info@ironbark.technology