

Steelcoat System - Technical Data Sheet

Product Description

A specially formulated, self etching, Acrylic cross linking polymer one coat coating system for weathered coil coated roofing substrates. Formulated using fungicides and light fast ceramic pigments for extended durability. Designed and tested for maximum weather durability. The Supercoat™ Steelcoat System is designed for use on weather coil coated steel products such as Coloursteel, Colourtile and Tuffcoat tiles.

Specifications

MSDS	016 - Version 1.0
Colour	16 standard colours
Vehicle Type	Acrylic
Solvent	Water
Touch dry time	1 - 3 hours at 20°C
Wet film thickness	250 microns
Solids Content	40.6 - 47.6%
Viscosity	80 - 100KU
Specific Gravity	1.18 - 1.3
Usual number of coats	1 (depending on substrate and colour density)
Toxicity	No added Chromites or Lead
Thinning & cleaning	Water
Coverage	3.5 - 4.0m ² /L depending on substrate profile and applicator
Pail type & size	Plastic 4L, 8L & 20L

Please Note

Do not apply at temperatures below 10°C or if it is likely to drop below 10°C during drying/curing time. Do not apply at temperatures over 30°C or if it is likely to go over 30°C during drying/curing time. Softens at temperatures over 70°C. Safe to use on surfaces that collect drinking water.

Manufacturer

Ironbark Technology Ltd
PO Box 2398, Dunedin, New Zealand.
Phone (03) 456 4222
info@ironbark.technology