

## Deckshield - Technical Data Sheet

### Product Description

Supercoat™ Deckshield is an Acrylic Thixotropic paste with graded aggregate for use on decks and roofs where general foot traffic may be expected. Supercoat™ Deckshield can be used as a final topcoat for the Supercoat™ Tanking Membrane System and is applied via hopper gun.

### Specifications

<b>MSDS</b>	<b>004 - Version 1.0</b>
<b>Appearance</b>	Grey
<b>Vehicle Type</b>	Acrylic
<b>Pigmentation</b>	Ceramic Pigments
<b>Solvent</b>	Water
<b>Finish</b>	Flat
<b>Colour</b>	Grey
<b>Touch dry time</b>	4 hours at 20°C
<b>Time to traffic</b>	24 hours at 20°C (dependant on substrate profile, applicator and climatic conditions)
<b>Wet film thickness</b>	1000 - 1500 microns
<b>Solids Content</b>	45%
<b>Viscosity</b>	95 - 105KU
<b>Specific Gravity</b>	1.03 - 1.4
<b>Usual number of coats</b>	2 wet on wet coats to ensure complete and even coverage and build is achieved over the Supercoat™ Tanking Membrane System
<b>Toxicity</b>	No added Chromites or Lead
<b>Thinning &amp; cleaning</b>	Water
<b>2 coat coverage</b>	0.9m <sup>2</sup> /L depending on substrate profile and applicator
<b>Pail type &amp; size</b>	Plastic 4L, 8L & 20L

### Please Note

Do not apply at temperatures below 10°C or if it is likely to drop below 10°C during drying/curing time. Do not apply at temperatures over 30°C or if it is likely to go over 30°C during drying/curing time. Softens at temperatures over 70°C.

### Manufacturer

**Ironbark Technology Ltd**  
PO Box 2398, Dunedin, New Zealand.  
Phone (03) 456 4222  
info@ironbark.technology